



US007794819B2

(12) **United States Patent**
Black et al.

(10) **Patent No.:** **US 7,794,819 B2**
(45) **Date of Patent:** **Sep. 14, 2010**

- (54) **ELASTIC COMPOSITE**
- (75) Inventors: **Kevin P. Black**, Rock Hill, SC (US);
Dickie J. Brewer, Clover, SC (US);
Donald H. Lester, Jr., Waxhaw, NC (US);
Thierry Marche, La Chapelle Basse Mer (FR)
- (73) Assignee: **Aplix, Inc.**, Charlotte, NC (US)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

4,935,287 A	6/1990	Johnson et al.	
4,978,570 A	12/1990	Heyn et al.	
5,057,097 A	10/1991	Gesp	
5,116,662 A *	5/1992	Morman	428/198
5,209,801 A	5/1993	Smith	
5,236,430 A	8/1993	Bridges	
5,393,599 A *	2/1995	Quantrille et al.	442/57
5,422,172 A	6/1995	Wu	
5,451,219 A	9/1995	Suzuki et al.	
5,591,152 A	1/1997	Buell et al.	
5,683,533 A	11/1997	Keighley et al.	
5,683,787 A	11/1997	Boich et al.	
5,763,041 A	6/1998	Leak et al.	

(21) Appl. No.: **11/840,407**

(22) Filed: **Aug. 17, 2007**

(65) **Prior Publication Data**
US 2008/0051748 A1 Feb. 28, 2008

(Continued)

Related U.S. Application Data

FOREIGN PATENT DOCUMENTS

- (60) Provisional application No. 60/839,998, filed on Aug. 24, 2006, provisional application No. 60/889,311, filed on Feb. 12, 2007.

DE 4008674 9/1991

- (51) **Int. Cl.**
B32B 5/04 (2006.01)
 - (52) **U.S. Cl.** **428/189**; 428/190; 428/194;
428/195.1; 428/198; 442/328; 442/329
 - (58) **Field of Classification Search** 442/328,
442/329; 428/189, 190, 194, 195.1, 198;
156/163, 182
- See application file for complete search history.

(Continued)

Primary Examiner—Elizabeth M Cole
(74) *Attorney, Agent, or Firm*—Hammer & Associates, P.C.

(56) **References Cited**


(57) **ABSTRACT**

U.S. PATENT DOCUMENTS

3,800,796 A	4/1974	Jacob
4,525,407 A	6/1985	Ness
4,761,324 A	8/1988	Rautenberg et al.
4,795,456 A	1/1989	Borgers et al.
4,834,741 A	5/1989	Sabee
4,886,511 A	12/1989	Korpman

An elastic composite includes a first nonwoven, a second nonwoven, and two elastic films sandwiched between the first and second nonwovens. The elastic composite also includes a lateral edge portion where the first nonwoven is bonded to the second nonwoven, a lane between the elastic films that is free of the elastic films, and a first bond joining the first nonwoven to the elastic film, and a second bond joining the second nonwoven to the elastic film. The elastic composite may be used as a component of a disposable garment.

20 Claims, 4 Drawing Sheets



US 7,794,819 B2

Page 2

U.S. PATENT DOCUMENTS

5,769,838 A 6/1998 Buell et al.
5,804,021 A 9/1998 Abuto et al.
5,882,769 A * 3/1999 McCormack et al. 428/152
6,069,097 A * 5/2000 Suzuki et al. 442/328
6,159,584 A 12/2000 Eaton et al.
6,221,483 B1 4/2001 Hilston et al.
6,255,236 B1 7/2001 Cree et al.
6,726,983 B2 4/2004 Erdos et al.
6,967,178 B2 * 11/2005 Zhou et al. 442/149
2003/0136497 A1 * 7/2003 Hamulski et al. 156/73.1

2005/0287892 A1 12/2005 Fouse et al.
2006/0292328 A1 * 12/2006 Baldauf et al. 428/77
2007/0249254 A1 10/2007 Mansfield

FOREIGN PATENT DOCUMENTS

EP 0630631 6/1993
EP 094133 9/1999
GB 2016262 A 9/1979
WO WO 9321879 11/1993

* cited by examiner




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9

1

ELASTIC COMPOSITE

RELATED APPLICATIONS

This application claims the benefit of earlier-filed, 5
co-pending U.S. Provisional application Nos. 60/839,998
filed Aug. 24, 2006 and 60/889,311 filed Feb. 12, 2007.

FIELD OF THE INVENTION

The instant invention is directed to an elastic composite for
use in disposable garments, particularly as a side panel (or
ear) or a tab of a disposable diaper.

BACKGROUND OF THE INVENTION

Disposable garments, for example diapers or training
pants, are known. Such garments may have side panels (or
ears) and/or tabs. The side panels and/or tabs may be made
from elastic composites. Elastic composites typically com- 20
prise various combinations of nonwovens and elastic materi-
als, each combination designed to obtain a specific solution to
a particular problem. Often, these elastic composites require
some type of mechanical work to activate the composite.

Examples of elastic composites (also known as elastic
laminates) may be found in U.S. Pat. Nos. 6,255,236 and
6,726,983. U.S. Pat. No. 6,255,236 discloses an elastic lami-
nate where two nonwovens sandwich an elastic web, and the
laminated has at least one elastic lane and at least one stiffened 25
lane. U.S. Pat. No. 6,726,983 discloses an elastic laminate
where two nonwovens sandwich an elastic film, and the elas-
tic film is extrusion coated onto one nonwoven and is ther-
mally bonded to the other nonwoven.

There is an on-going effort in the disposable garment 35
industry to provide new elastic composites with a balance of
physical and esthetic properties and cost. Accordingly, there
is a need for new elastic composites.

SUMMARY OF THE INVENTION

An elastic composite includes a first nonwoven, a second
nonwoven, and two elastic films sandwiched between the first
and second nonwovens. The elastic composite also includes a
lateral edge portion where the first nonwoven is bonded to the 45
second nonwoven, a lane between the elastic films that is free
of the elastic films, and a first bond joining the first nonwoven
to the elastic films, and a second bond joining the second
nonwoven to the elastic films. The elastic composite may be
used as a component of a disposable garment. 50

DESCRIPTION OF THE DRAWINGS

For the purpose of illustrating the invention, there is shown
in the drawings a form that is presently preferred; it being
understood, however, that this invention is not limited to the
precise arrangements and instrumentalities shown.

FIG. 1 is a schematic illustration of a representative dis-
posable garment, e.g., a diaper.

FIG. 2 is a schematic illustration of a second representative
disposable garment, e.g., a diaper.

FIG. 3 is a top plan view of an embodiment of the instant
invention, parts broken away for clarity.

FIG. 4 is an exploded sectional view of a first embodiment 65
of the instant invention taken along sectional lines A-A of
FIG. 3.

2

FIG. 5 is an exploded sectional view of a second embodi-
ment of the instant invention taken along sectional lines A-A
of FIG. 3.

FIG. 6 is an exploded sectional view of a third embodi-
ment of the instant invention taken along sectional lines A-A
of FIG. 3.

FIG. 7 is an exploded sectional view of a fourth embodi-
ment of the instant invention taken along sectional lines A-A
of FIG. 3.

10 FIG. 8 is an exploded sectional view of a fifth embodi-
ment of the instant invention taken along sectional lines A-A of
FIG. 3.

FIG. 9 is a schematic illustration of a process for making
the instant invention.

15

DESCRIPTION OF THE INVENTION

Referring to the drawings, wherein like elements have like
numerals, there is shown in FIGS. 1 and 2 representative
disposable garments, diapers 10 and 30.

In FIG. 1, diaper 10 generally comprises a rear waist por-
tion 12, a front waist portion 14, and an interconnecting
portion 16. At the lateral edges of the rear waist portion 12,
there are affixed side panels (or ears) 18. At the distal ends of
the side panels 18, tabs 20 may be affixed thereto. At the distal 25
ends of tab 20, fastening device 22 may be affixed thereto. On
the exterior surface of front waist portion 14, a mating fas-
tening device 24 may be disposed (shown as two elements,
but may be a continuous element). Fastening device 22 and
mating fastening device 24 co-operate to releasably secure
diaper 10 about a wearer, as is well known. Fastening device
22 and mating fastening device 24 may be any known fasten-
ing mechanism. Such known fastening mechanisms include,
but are not limited to, hook and loop fasteners and adhesive
fasteners. In diaper 10, side panels 18 may be elastic (e.g.,
stretchable in a direction away from rear waist portion 12), so
that the diaper may be securely fit to the wearer, and tabs 20
may be non-elastic.

In FIG. 2, diaper 30 generally comprises a rear waist por-
tion 32, a front waist portion 34, and an interconnecting
portion 36. At the lateral edges of the rear waist portion 32,
there are affixed side panels (or ears) 38. At the distal ends of
the side panels 38, tabs 40 may be affixed thereto. At the distal 45
ends of tab 40, fastening device 42 may be affixed thereto. On
the exterior surface of front waist portion 34, a mating fas-
tening device 44 may be disposed (shown as two elements,
but may be a continuous element). Fastening device 42 and
mating fastening device 44 co-operate to releasably secure
diaper 30 about a wearer, as is well known. Fastening device
42 and mating fastening device 44 may be any known fasten-
ing mechanism. Such known fastening mechanisms include,
but are not limited to, hook and loop fasteners and adhesive
fasteners. In diaper 30, side panels 18 may be non-elastic, and
tabs 20 may be elastic (e.g., stretchable in a direction away
from rear waist portion 32), so that the diaper may be securely
fit to the wearer. 50

Referring to FIG. 3, the instant invention, an elastic com-
posite 50, is shown. Elastic composite 50 generally comprises
a first (or bottom) nonwoven 54, a second (or upper) non-
woven 56, and a first (or right) elastic film 58 and second (or
left) elastic film 60 sandwiched between the first nonwoven
54 and second nonwoven 56. The elastic composite 50 gen-
erally comprises two lateral edge portions 62, two stretch
zones 64 and a lane 66 (lane 66 is divided by a center line 52
which is shown for reference). In the lateral edge portion 62,
the first nonwoven 54 and the second nonwoven 56 may be
bonded together (discussed in greater detail below). In the

stretch zone **64**, the first and second nonwovens **54**, **56** may be bonded to the upper and lower surfaces of the elastic films **58**, **60** (discussed in greater detail below).

The first and second nonwovens **54**, **56** may be identical materials. These nonwovens may be any nonwoven. In one embodiment, the nonwoven has a basis weight in the range of 10-40 g/m², and in another embodiment, in the range of 22-30 g/m². The nonwoven, in one embodiment, is inelastic and highly extensible in the cross machine direction (CD). In one embodiment, the nonwoven has a CD extension at peak load of at least 200%. These nonwovens may be further characterized, in another embodiment, by their CD/MD (CD-cross machine or transverse direction; MD-machine direction) elongation ratio which may be at least 1:1, or at least 3:1, or in the range of 3-6:1, or in the range of 4-5:1. In one embodiment, the nonwoven is a point-bonded, carded nonwoven or spunlaced nonwoven produced from staple fibers. The staple fibers may be any material, for example, polyester (e.g., PET), polyolefin (e.g., PP), or a blend of both. The nonwoven may have apertures. An example of the point-bonded carded nonwoven is FPN 571D available from Fiberweb of Simpsonville, S.C. or SAWABOND 4132 (22 g/m²) from Sandler AG of Schwarzenbach, Germany. An example of the spunlaced nonwoven is SAWATEX® 2628 available from Sandler AG of Schwarzenbach, Germany.

The elastic films **58**, **60** are, in one embodiment, identical to one another. The elastic films may be made from any elastomeric polymer. In one embodiment, the elastomeric polymers may be styrenic block copolymers. Styrenic block copolymers include, but are not limited to, SIS (styrene-isoprene-styrene) block copolymers, SBS (styrene-butene-styrene) block copolymers, and combinations thereof. The elastic film may have a basis weight, in one embodiment, of 40-100 g/m², and in another, 50-70 g/m². The elastic film may be further characterized by CD elongation of at least 200%.

The adhesive used in the bonding discussed above may be any adhesive. In one embodiment, the adhesive is a hot melt, non-elastic adhesive. Alternatively, adhesive may be replaced with bonding (e.g., thermal, ultrasonic, and/or infrared with or without binder fibers in the nonwoven).

The instant invention, elastic composite **50**, shall be discussed in further detail below with regard to the embodiments shown in FIGS. 4-8.

In FIG. 4, elastic composite **50'** is shown. In lateral edge portions **62**, the first nonwoven **54** and the second nonwoven **56** are bonded together via lateral edge bonds **68**. The lateral edge bonds **68** are formed from the adhesive discussed above. While in each lateral edge portion **62** there is shown two layers of adhesive (forming bonds **68**), the invention is not so limited and, for example, a single layer of adhesive (applied to either nonwoven) may be used. Lateral edge bonds **68**, in one embodiment, may be a continuous layer of adhesive (i.e., the adhesive covers the length and width of the lateral edge portions), whereby the nonwovens, which are inelastic but extensible, are generally fixed (i.e., prevented or substantially prevented from extension). Lateral edge bonds **68**, in another embodiment, may be in the form of a grid or cross-hatching of lines of adhesive, or any other pattern intended to generally fix the nonwovens in the lateral edge portions **62**. In one embodiment where the width of the elastic composite is 170 mm, the adhesive weight of the lateral edge bonds **68** is 8-9 g/m².

Likewise, in lane **66**, the first nonwoven **54** and the second nonwoven **56** are bonded together via lane bonds **72**. The lane bonds **72** are formed from the adhesive discussed above. While in lane **66** there is shown two layers of adhesive (forming bonds **72**), the invention is not so limited and, for example,

a single layer of adhesive (applied to either nonwoven) may be used. Lane bonds **72**, in one embodiment, may be a continuous layer of adhesive (i.e., the adhesive covers the length and width of the lane), whereby the nonwovens, which are inelastic but extensible, are generally fixed (i.e., prevented or substantially prevented from extension). Lane bonds **72**, in another embodiment, may be in the form of a grid or cross-hatching of lines of adhesive, or any other pattern intended to generally fix the nonwovens in the lane portion **66**. In one embodiment where the width of the elastic composite is 170 mm, the adhesive weight of the lane bond **78** is 2-3.2 g/m².

In stretch zones **64**, the first nonwoven **54** and the second nonwoven **56** are bonded to elastic films **58**, **60** via stretch zone bonds **70**. The stretch zone bonds **70** are located between the first nonwoven **54** and the elastic films **58**, **60**, and between the second nonwoven **56** and the elastic films **58**, **60**, as shown. The stretch zone bonds **70** are formed from the adhesive discussed above. The stretch zone bond **70** consists of a plurality of adhesive bonds, whereby when the elastic composite is stretched in the CD, the nonwoven may extend with the elastic film, and when the elastic composite is relaxed, the nonwoven may bulk. The stretch zone bonds **70**, in one embodiment, may be a plurality of continuous lines of adhesive extending in the MD (in the drawing, this is illustrated by a horizontal line of dots). The stretch zone bond **70**, in another embodiment, may be a plurality of discontinuous (e.g., dots) lines of adhesive extending in the MD (in the drawing, this is illustrated by a horizontal line of dots). The elastic films **58**, **60** may extend to the lateral edges of the stretch zone **64** or may extend slightly over the lateral edges of the stretch zone **64**. Instead of lines of adhesive, a continuous film of adhesive of various weights/volumes/densities of adhesives may be used (e.g., a pattern of high density adhesive lines with lower densities there between). In one embodiment, the lines of adhesive may have a width in the range of 0.5-1.0 mm or 0.5-0.55 mm. In one embodiment, the center-to-center line of adhesive spacing may be in the range of 2.0-2.5 mm.

In FIG. 5, elastic composite **50"** is shown. Elastic composite **50"** is the same as elastic composite **50'** (of FIG. 4), except as follows. A stiffener **74** is added to lane **66** between the first nonwoven **54** and the second nonwoven **56**. Stiffener **74** is added to provide additional mechanical strength to lane **66**. Lane **66** may be the portion of the elastic composite that is affixed to the disposable garment or the fastener may be affixed thereto, and as such may require additional mechanical strength to facilitate attachment to the garment in assembly of the garment and/or use of the garment. Stiffener **74** is bonded to the first nonwoven **54** and the second nonwoven **56** via lane bonds **72**, as discussed above. Stiffener **74** is a non-extensible material (non-extensible with regard to the elastic films **58**, **60**). Stiffener **74** may be a film or nonwoven. In elastic composite **50"**, stiffener **74** extends slightly beyond the lateral edges of lane **66** and overlaps (but may not be bonded thereto) the elastic films **58**, **60**.

In FIG. 6, elastic composite **50'''** is shown. Elastic composite **50'''** is the same as elastic composite **50"** (of FIG. 5), except as follows. Stiffener **74** does not overlap elastic films **58**, **60**, and when the elastic composite **50'''** is assembled, the lateral edges of stiffener **74** are adjacent to or abut with their respective lateral edge of the elastic films.

In FIG. 7, elastic composite **50''''** is shown. Elastic composite **50''''** is the same as elastic composite **50'** (of FIG. 4), except as follows. In elastic composite **50''''**, elastic films **58**, **60** are replaced with film **76**. Film **76** has three zones, two lateral stretch portions **78** (corresponding to the stretch zones **64**) and a center portion **80** therebetween (corresponding to

5

lane 66). The lateral stretch portions 78 are elastic and the center portion 80 is inelastic. Film 76 is a unitary material and may be made by co-extrusion.

In FIG. 8, elastic composite 50A is shown. Elastic composite 50A is similar to the foregoing elastic composites, except as follows. Elastic composite 50A has no lane 66. Instead, elastic composite 50A includes elastic film 82 (same materials of construction as prior elastic films) which may be adhered to the first nonwoven 54 and second nonwoven 56 via stretch zone bonds 70, as shown. Elastic composite 50A consists of two lateral edge portions 62 and an intermediate stretch zone 64.

Referring to FIG. 9, a process 100 for making elastic composite 50 is illustrated. In extrusion step 102, the elastic films 58, 60 or film 76 is made from polymeric resins in to the extruded material. In cooling step 104, the extruded material is cooled and solidified. In laminating step 106, elastic films 58, 60 or film 76 (and/or stiffener 74 as needed) are laminated between nonwovens 54, 56 (nonwovens 54, 56 being provided from supplies 108). Typically, there is no tension in the laminator (except for the slight tensions necessary to move the films and nonwovens therethrough). Optionally, however, a tension (in the MD) may be added to 'neck down' the nonwoven prior to lamination to the film. In stiffening step 110, lane 66 (and/or lateral edge portions 62) may be subject to calendaring (either heated or nonheated rollers) to ensure firm bonding therein. Finally, in take-up step 112, the elastic composite 50 may be subjected to inspection, edge trim, winding up, and/or packaging.

When used in the disposable garment, the elastic composite may be cut along center line 52; so that one portion may be used on the right side of the garment and the other portion may be used on the left side of the garment. When elastic composite 50 is used as a side panel (or ear), the elastic composite should have a CD elongation of at least 140%. When the elastic composite 50 is used as a tab, the elastic composite should have a CD elongation of at least 35% (to obtain this elongation, it may be necessary to use a continuous adhesive layer for stretch zone bonds 70). The lane portion of the elastic composite is used to fasten the elastic composite to the garment.

The present invention may be embodied in other forms without departing from the spirit and the essential attributes thereof, and, accordingly, reference should be made to the appended claims, rather than to the foregoing specification, as indicated the scope of the invention.

We claim:

1. An elastic composite comprising:

a first nonwoven, said first nonwoven being extensible, but inelastic, said first nonwoven having a CD extension at peak load of at least 200%, said first nonwoven being further characterized by a CD/MD elongation ratio of at least 3:1, said first nonwoven being a point-bonded carded nonwoven made of staple fibers or a spunlaced nonwoven, said first nonwoven having a basis weight in the range of 10-40 g/m²,

a second nonwoven, said second nonwoven being extensible, but inelastic, said second nonwoven having a CD extension at peak load of at least 200%, said second nonwoven being further characterized by a CD/MD elongation ratio of at least 3:1, said second nonwoven being a point-bonded carded nonwoven made of staple fibers or a spunlaced nonwoven, said second nonwoven having a basis weight in the range of 10-40 g/m²,

a first elastic film and a second elastic film, said first elastic film and said second elastic film being laterally spaced apart from one another and sandwiched between said

6

first nonwoven and said second nonwoven, said first elastic film and said second elastic film being bonded to said first nonwoven and said second nonwoven, respectively, by a plurality of continuous lines of a hot melt adhesive extending in the MD direction when said first elastic film and said second elastic film being non-tensioned,

a non-extensible material between said first elastic film and said second elastic film and being sandwiched between and bonded to said first nonwoven and said second nonwoven,

whereby when the elastic composite is stretched in the CD direction, said nonwovens extend with said elastic films and when the elastic composite is relaxed, said nonwovens bulk.

2. The elastic composite of claim 1 wherein said CD/MD elongation ratio being in the range of 4-5:1.

3. The elastic composite according to claim 1 wherein said first nonwoven or said second nonwoven being a spunlaced nonwoven.

4. The elastic composite according to claim 1 wherein said first elastic film or said second elastic film or both comprising a styrenic block co-polymer.

5. The elastic composite according to claim 1 wherein said first elastic film or said second elastic film or both having a basis weight in the range of 50-70 g/m².

6. The elastic composite according to claim 1 wherein said first elastic film or said second elastic film or both being characterized by a CD elongation of at least 200%.

7. The elastic composite according to claim 1 wherein said hot melt adhesive being a non-elastic adhesive.

8. The elastic composite according to claim 1 wherein a line of said plurality of continuous lines having a width in the range of 0.5-1.0 mm.

9. The elastic composite according to claim 1 wherein a line of said plurality of continuous lines having a width in the range of 0.5-0.55 mm.

10. The elastic composite according to claim 1 wherein a center-to-center spacing of said plurality of continuous lines being in the range of 2.0-2.5 mm.

11. An elastic composite comprising:

a first nonwoven, said first nonwoven being extensible, but inelastic, said first nonwoven having a CD extension at peak load of at least 200%, said first nonwoven being further characterized by a CD/MD elongation ratio of at least 3:1, said first nonwoven being a point-bonded carded nonwoven made of staple fibers or a spunlaced nonwoven, said first nonwoven having a basis weight in the range of 10-40 g/m²,

a second nonwoven, said second nonwoven being extensible, but inelastic, said second nonwoven having a CD extension at peak load of at least 200%, said second nonwoven being further characterized by a CD/MD elongation ratio of at least 3:1, said second nonwoven being a point-bonded carded nonwoven made of staple fibers or a spunlaced nonwoven, said second nonwoven having a basis weight in the range of 10-40 g/m²,

a first elastic film and a second elastic film, said first elastic film and said second elastic film being laterally spaced apart from one another and sandwiched between said first nonwoven and said second nonwoven, said first elastic film and said second elastic film being bonded to said first nonwoven and said second nonwoven, respectively, by a plurality of continuous lines of a hot melt adhesive extending in the MD direction when said first elastic film and said second elastic film being non-tensioned,

7

a non-extensible material between said first elastic film and said second elastic film and being sandwiched between said first nonwoven and said second nonwoven and bonded to said first nonwoven and said second nonwoven with a hot melt adhesive,

whereby when the elastic composite is stretched in the CD direction, said nonwovens extend with said elastic films and when the elastic composite is relaxed, said nonwovens bulk.

12. The elastic composite of claim 11 wherein said CD/MD elongation ratio being in the range of 4-5:1.

13. The elastic composite according to claim 11 wherein said first nonwoven or said second nonwoven being a spunlaced nonwoven.

14. The elastic composite according to claim 11 wherein said first elastic film or said second elastic film or both comprising a styrenic block co-polymer.

8

15. The elastic composite according to claim 11 wherein said first elastic film or said second elastic film or both having a basis weight in the range of 50-70 g/m².

16. The elastic composite according to claim 11 wherein said first elastic film or said second elastic film or both being characterized by a CD elongation of at least 200.

17. The elastic composite according to claim 11 wherein said each hot melt adhesive being a non-elastic adhesive.

18. The elastic composite according to claim 11 wherein a line of said plurality of continuous lines having a width in the range of 0.5-1.0 mm.

19. The elastic composite according to claim 11 wherein a line of said plurality of continuous lines having a width in the range of 0.5-0.55 mm.

20. The elastic composite according to claim 11 wherein a center-to-center spacing of said plurality of continuous lines being in the range of 2.0-2.5 mm.

* * * * *